

ChopVantage® HP 3293

Product Description

ChopVantage HP 3293 chopped strands from NEG are suitable for use in all polypropylene (PP) systems and have been developed for applications that require whiteness and high mechanical properties. The product is designed for components in the appliance market where mechanical properties are critical. **CHOPVANTAGE HP 3293** chopped strand products have an excellent performance in heat ageing and hot detergent resistance. The new chemistry of **CHOPVANTAGE HP 3293** chopped strands creates an excellent performance in hot detergent-resistant applications.

User Benefits

- Compatible with a wide range of PP resins.
- Superior dry flow performance.
- Provides uniform dispersion during the compounding process.
- Offers a good white color in natural grade compounds.
- Excellent color stability in hot detergent testing and heat ageing testing.
- Provides an optimum balance of sizing functions.
- USA Food and Drug Administration and EU 10/2011 compliance for repeated-use food contact applications.
- APE free, as well as compliant with French potable water contact regulations.
- Product supported by NEG's extensive technical resources.
- Manufacturing facilities operate quality management systems that comply with ISO 9001:2015 requirements.

Type of Fiber	E-Glass (ASTM D 578-05)
Type of Sizing	Silane
Nominal Fiber Diameter (µm)	13.0
Nominal LOI (%)	EU: 1.0
Nominal Chop Length (mm)	EU: 4.5

Packaging

- Big bag with 1,000/1,100 kg. Other weights on request.
- Smaller packaging available on request.
- Octabins available in Europe.

Storage

These products should be stored in a cool and dry area. Protect product from all sources of water at all times. A First-in-First-Out (FIFO) stock control system is recommended to minimize the influence of storage conditions. Prior to use, products should be conditioned in the work area for a minimum of 24 hours. If contents of a package unit are partially used, the unit should be closed until the next use. To ensure optimal performance, retesting for mechanical properties and feeding behavior is recommended for products stored more than one year from the original production date.

More Information

<https://www.neg.co.jp/inquiry/>

<https://www.neg.co.jp/en/inquiry/>