

ChopVantage® HP 3730

Product Description

ChopVantage HP 3730 chopped strands from NEG are designed for reinforcement of polybutylene terephthalate (PBT) thermoplastic polyester. The *CHOPVANTAGE* HP 3730 chopped strands can be used for high-performance applications in transportation, electric and electronic appliances and computer housing and components – where mechanical properties play an important role. The product combines dry as molded (DAM) properties with outstanding with outstanding hydrolysis resistance. It is an excellent fit for high throughput compounding systems due to its high flow characteristics.

User Benefits

- Suitable for a wide range of thermoplastic resins, including PBT, PET, PC, POM, PLA and PPS.
- Excellent mechanical properties after hydrolysis.
- Exhibits very good Dry As Molded mechanical properties.
- Superior dry flow performance which contributes to high compounding rates.
- Unique properties in polylactide (PLA) resin systems.
- Wide range of versatility with respect to feeding and handling.
- Provides uniform dispersion during the compounding process.
- U.S. Food and Drug Administration compliance for repeated-use food contact applications
- APE Free, as well as, French and German potable water contact compliance.
- Product supported by NEG's extensive technical resources.
- Manufacturing facilities operate quality management systems that comply with ISO 9001:2015 requirements.

Type of Fiber	E-Glass (ASTM D 578-05)
Type of Sizing	Silane
Nominal Fiber Diameter	10
LOI (%)	NA: 0.85 EU: 0,70
Standard Cut Length (mm)	NA: 3.2 EU: 4.5

Packaging

Americas

- 1,000 kg Bulk Bag
- 612 kg (1,350 lbs) Corrugated Carton

Europe

- 1,000 / 1,100 kg bigbags
- 1,000 / 1,100 kg octabins

Storage

These products should be stored in a cool and dry area. Protect product from all sources of water at all times. A First-in-First-Out (FIFO) stock control system is recommended to minimize the influence of storage conditions. Prior to use, products should be conditioned in the work area for a minimum of 24 hours. If contents of a package unit are partially used, the unit should be closed until the next use. With proper storage, there are no known limitations on the shelf life of the product. To ensure optimal performance, retesting for mechanical properties and feeding behavior is recommended for products stored more than two years from the original production date.

More Information

<https://www.neg.co.jp/inquiry/>

<https://www.neg.co.jp/en/inquiry/>