



Direct Roving Fiber Glass
HYBON[®]

2006



Product Description

HYBON 2006 roving from NEG is made of E-Glass fiber and is compatible with amine and anhydride-cured epoxy resin systems. **HYBON 2006** roving is designed for filament winding and pultrusion applications, which require good wet out and saturation consistency together with good abrasion resistance and processing characteristics. It is suitable for applications such as piping in oil fields, CO₂ gathering systems, and pressure cylinders. Each package is in a wrap film with each pallet stretch wrapped to protect the fiber glass roving from dirt and moisture.

User Benefits

- Tolerates filament winding processing conditions that ordinarily result in broken filaments.
- Multi-resin compatibility eliminates the need to change creels when changing resin systems, thus minimizing downtime.
- Rapid and complete wet out.
- High wet and dry abrasion resistance.
- Excellent package transfer efficiency through the use of an outer adhesive film.
- Supported by NEG's extensive technical resources.
- Manufacturing facilities operate quality management systems that comply with ISO 9001:2015 requirements.
- Germanischer Lloyd (GL) certified.

Packaging

- 48 packages/pallet
- 20 kg (44 lbs.) /package



GLASS FOR FUTURE



Nippon Electric Glass

Product Information

Type of Fiber	E-Glass (ASTM D 578-05, Section 4.2.2)			
Type of Sizing	Silane			
Roving Tex, nominal (g/km)	735	1100	1984	2200
Roving Yield, nominal (yd/lb)	675	450	250	225
Average Fiber Diameter (µm)	14	17	23	23

Other Tex/Yield options are available upon request.
Contact your NEG Account Manager.

Storage

These products should be stored in a dry area with ambient temperature and relative humidity, optimally from 20°C to 25°C and between 50% and 70%, respectively. Protect product from all sources of water at all times. A First-In-First-Out (FIFO) stock control system is recommended to minimize the influence of storage conditions. Prior to use, products should be conditioned in the work area for a minimum of 24 hours. If contents of a package unit are partially used, the unit should be closed until the next use. With proper storage, there are no known limitations on the shelf life of the product. To insure optimal performance, retesting is recommended for products stored more than two years from the initial production date.

Caution

To avoid the possibility of potential injury, maintain column stability by limiting pallet stacking to two (2) high as noted on individual shipping containers.

NOTE: This data is offered for informational purposes only in the selection of a composite reinforcement. The information contained in this bulletin is based on actual laboratory data. We believe that this information is reliable, but do not guarantee its applicability to the process of the user or assume any liability arising out of its use or performance. The user, by accepting the products described, agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial laminates when using this or any other reinforcement. *Because of numerous factors affecting the results, we make no warranty of any kind, expressed or implied, including those of merchantability and fitness for a particular purpose. Statements in this document shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code, or insurance regulation.*

More Information

<http://www.neg.co.jp/inquiry/>

<http://www.neg.co.jp/en/inquiry/>