

Product Description

Hybon™ 2025 roving from NEG is a continuous filament, single-end strand roving designed to reinforce polyester, vinyl ester and epoxy resin systems. HYBON 2025 roving may be used in pultrusion applications. It offers rapid wetout and saturation with low resin demand and can be processed free of catenary. HYBON 2025 roving consists of multiple filaments of glass fiber honed with a multi-compatible sizing into a single, splice-free strand. Each package is in a wrap film with each pallet stretch wrapped to protect the fiber glass roving from dirt and moisture.

User Benefits

- Multi-compatible with polyester, vinyl ester and epoxy resins.
- Excellent unwinding performance and transfer from package to package.
- Single-end roving that catenary-free and abrasion resistant.
- Low resin demand during subsequent processing.
- Consistent tex control and surface sizing system.
- Rapid, complete and consistent wet out.
- Manufacturing facilities operate quality management systems that comply with ISO 9001:2015 requirements.

Type of Fiber	E-Glass (ASTM D 578-05, Section 4.2.2)		
Type of Sizing	Silane		
Roving Tex, nominal (g/km)	1100	4400	8800
Roving Yield, nominal (yd/lb)	450	113	56
Average Fiber Diameter (µm)	17	24	34
Other Tex/Yield options are available upon request.			

Storage

These products should be stored in a cool and dry area. Protect product from all sources of water at all times. A First-in-First-Out (FIFO) stock control system is recommended to minimize the influence of storage conditions. Prior to use, products should be conditioned in the work area for a minimum of 24 hours. If contents of a package unit are partially used, the unit should be closed until the next use. With proper storage, there are no known limitations on the shelf life of the product. To ensure optimal performance, retesting for mechanical properties and feeding behavior is recommended for products stored more than two years from the original production date. To avoid the possibility of potential injury, maintain column stability by limiting pallet stacking to two (2) high as noted on individual shipping containers.

More Information

<https://www.neg.co.jp/inquiry/>

<https://www.neg.co.jp/en/inquiry/>

NEG reserves the right to modify this document without prior notice.

NOTE: This data is offered for informational purposes only in the selection of a composite reinforcement.

Hybon™ and TufRov™ are trademarks of Electric Glass Fiber America, LLC.

Mechanical Properties

Impregnated Strand Tensile Testing

(ASTM D2343)

Tensile Strength (MPa/ksi) = 2790/405
 Glass Content by Weight (%) = 57.9

Interlaminar Shear Strength (ASTM D2344)

Anhydride Cured Epoxy

Horizontal Shear Dry (MPa/ksi) = 71.7/10.4
 Horizontal Shear Wet*(MPa/ksi) = 70.3/10.2
 Strength Retention (%) = 98.0

Unsaturated Polyester

Horizontal Shear Dry (MPa/ksi) = 68.7/9.96
 Horizontal Shear Wet*(MPa/ksi) = 60.6/8.79
 Strength Retention (%) = 88.2

*6 Hour water boil conditioning

Packaging

- 48 packages/pallet
- 20 kg (44 lbs.) /package