

ChopVantage® HP 3610XM

NEG Nippon Electric Glass Co., Ltd.

Product Description

ChopVantage HP 3610XM chopped strands from NEG are designed to reinforce a wide range of polyamide (PA) formulations. *CHOPVANTAGE* HP 3610XM chopped strands offer superior dry as molded properties, resistance to ethylene glycol based coolant systems and excellent performance in impact modified resins. The unique XM glass formulations utilized in this product provides highly desirable high fiber toughness as compared to traditional E-Glass. This results in improved residual fiber length after molding and thereby improving the physical properties of the molded system. The sizing of *CHOPVANTAGE* HP 3610XM is designed for high throughput systems due to its excellent flow characteristics and low viscosity during extrusion and molding.

User Benefits

- Suitable for a wide range of polyamide thermoplastic resin systems: PA6, PA66, PA46, PA610 and PA612.
- Low Viscosity during compounding supports high throughput processes
- Provides uniform dispersion during the compounding process.
- Excellent mechanical properties in combination with environmentally friendly flame retardants.
- High impact properties and fatigue resistance.
- High hydrolysis resistance properties in several long-life coolant (LLC) systems.
- U.S. Food and Drug Administration and EU 10/2011 compliance for repeated-use food contact applications.
- APE Free, as well as, French and German potable water contact compliance.
- Product supported by NEG's extensive technical resources.
- Manufacturing facilities operate quality management systems that comply with ISO 9001:2015 requirements.

Type of Fiber	E-Glass (ASTM D 578-05)
Type of Sizing	Silane
Nominal Fiber Diameter (µm)	10
Nominal LOI (%)	NA: 0.75
Nominal Chop Length (mm)	NA: 3.2

Packaging

- 1,000 kg Bulk Bag
- 612 kg (1,350 lbs) Corrugated Carton

Storage

These products should be stored in a cool and dry area. Protect product from all sources of water at all times. A First-in-First-Out (FIFO) stock control system is recommended to minimize the influence of storage conditions. Prior to use, products should be conditioned in the work area for a minimum of 24 hours. If contents of a package unit are partially used, the unit should be closed until the next use. With proper storage, there are no known limitations on the shelf life of the product. To ensure optimal performance, retesting for mechanical properties and feeding behavior is recommended for products stored more than two years from the original production date.

More Information

<https://www.neg.co.jp/inquiry/>

<https://www.neg.co.jp/en/inquiry/>

NEG reserves the right to modify this document without prior notice.